

LDPE-R natur

(typical material properties)

<i>Physical and mechanical properties:</i>	<i>method of measurement</i>	<i>unit</i>	<i>value</i>
ITT (190°C / g/10 min)	ISO 1133	g/10 min	1,5 - 2,2
Elongation at break	ISO 527/1A	%	min.180
Tensile strength at yield	ISO 527/1A	MPa	min.14

<i>Thermal properties :</i>	<i>method of measurement</i>	<i>unit</i>	<i>value</i>
Softening temperature VICAT	ISO 306	°C	85
Melting temperature	ISO 11357	°C	102